

# REGULAR SERIES

FEATURES	STANDARD	PLANKS	HERRINGBONE
Floorcovering	EN 649	Heterogeneous LVT floorcovering	Heterogeneous LVT floorcovering
Completion		Matte particle laquer	Matte particle laquer
Design		Wood	Wood
Embossing		Universal Embossed	Universal Embossed
Colours		8	8
Dimension	EN 427	121,90x22,80 cm	60,96x15,24 cm
Bevelling		All sides	All sides
Content		12 pieces (3,345 m <sup>2</sup> )	36 pieces (3,345 m <sup>2</sup> )
Article numbers		2510   2540   2550   2560   <i>Regular</i> <sup>1</sup> 3010   3020   3030   3040   <i>Regular</i> <sup>2</sup>	6021   6024   6025   6026   <i>Regular</i> <sup>1</sup> 6031   6032   6033   6034   <i>Regular</i> <sup>2</sup>
Weight	EN 430	ca. 4315 g/m <sup>2</sup>	ca. 4315 g/m <sup>2</sup>
Thickness	EN 428	2,5 mm	2,5 mm
Thickness PU	EN 429	0,55 mm	0,55 mm
Classification	EN 685	23, 33, 42	23, 33, 42
Fire classification	EN 13501	Bfl-S1	Bfl-S1
Slipresistance	DIN 51130 EN 13893	R9 DS	R9 DS
Weargroup	EN 649	T	T
Residual indentation	EN 433	< 0,1 mm	< 0,1 mm
Dimension stability	EN 434	< 0,1%	< 0,1%
Soundreduction	EN140-8	ca. 5 dB(A)	ca. 5 dB(A)
Thermal conductivity	EN12667 DIN 52612	0,02 m <sup>2</sup> k/w	0,02 m <sup>2</sup> k/w
Electrical conductivity	EN 1081	app 10 <sup>11</sup> Ohm	app 10 <sup>11</sup> Ohm
Suitable for castor chairs	EN 425	Yes, type W	Yes, type W
Floor heating	EN14041	Yes, max. 27 °C	Yes, max. 27 °C
Colourfastness	ISO 105-B02	6> Grade	6> Grade
Resistance to chemicals	EN 423 EN ISO 26987	Yes, see 1	Yes, see <sup>1</sup>
Odor control	ISO 16000-28	Suisse Norm SNV	Suisse Norm SNV
AgBB VOC test		Approved	Approved
REACH regulation (EC)		1907/2006	1907/2006
CE, AGBB, Dibt, Eurofins, Floorscore, A+, ISO9001, ISO14001		Yes	Yes

<sup>1</sup> Resistance depending on concentration and exposure time, with prolonged action of oils, fats, acids, alkalis and other aggressive chemicals please contact us.

